

## **NITRO STRETCH FILM**

## **Hi-Stretch Conventional Machine Films**

Properties						
Film Thickness (gauge)		63	70	80		
Tensile Strength (Mpa)	MD TD	≥ 44 ≥ 28	≥ 46 ≥ 31	≥ 50 ≥ 33	ASTM D 882	
Elongation (%)	MD TD	≥ 440 ≥ 580	≥ 430 ≥ 555	≥ 450 ≥ 575	ASTM D 882	
Stretch Level (%)		≥ 250	≥ 250	≥ 220	Highlight Tester	
Other Specification		,				
Paper Core Length		Tolerance ± 2.0 m	Tolerance ± 2.0 mm			
Paper Core Thickness		Tolerance ± 0.3 m	Tolerance ± 0.3 mm			
Film Width		Tolerance ± 2.0 m	Tolerance ± 2.0 mm			
Film Thickness		Tolerance ± 1.5 μn	Tolerance ± 1.5 μm			
Storage Conditions	Store in a clean, dry place at room temperature. Avoid temperature and humidity extremes.					
					eness are not guaranteed. Before using ligations to replacement or at its option	

reimbursement of the purchase price of products shown to the seller's satisfaction to have been defective at the time the seller sold it.